

Premium appearance grade materials in a range of strengths for cookware and appliance applications.

| Property | Test Method, Unit | Properties | Test Method, Unit | Properties |
|---|--------------------------------|-------------|----------------------------|------------|
| Physical and Mechanical Properties | | | | |
| Impact Strength | ASTM D256, FT- LBS/IN | 3 – 4 | ISO-179, kJ/m ² | 15 – 20 |
| Flexural Strength | ASTM D790, PSI | 13 – 15,000 | ISO-178, MPa | 90 – 103 |
| Flexural Modulus | ASTM D790, 10 ⁶ PSI | -- | ISO-178, GPa | -- |
| Tensile Strength | ASTM D638, PSI | 5 – 6,000 | ISO-527, MPa | 34 |
| Compressive Strength | ASTM D695, PSI | 18 – 20,000 | ISO-604, MPa | 124 – 138 |
| Water Absorption | ASTM D570, % | 0.07 | ISO-62, % | 0.07 |
| Specific Gravity | ASTM D792, G/CM ³ | 1.90 | ISO-1183, -- | 1.90 |
| Shrinkage | ASTM D955, IN/IN | 0.001 | ISO-2577, % | 0.1 |
| Hardness | ASTM D2583, Barcol | 25 – 35 | ASTM D2583, Barcol | 25 – 35 |
| Bulk Factor App. | ASTM D1895, -- | 1 | ASTM D1895, -- | 1 |
| Electrical Properties | | | | |
| Dielectric Strength | ASTM D149, kV/in | 320 | ISO-243, kV/mm | 12 |
| Arc Resistance | ASTM D495, Seconds | -- | ASTMD495, Seconds | -- |
| Thermal & Flame Retardant Properties | | | | |
| Heat Deflection Temperature @ 264PSI | ASTM D648, °F | > 500 | ISO-75, °C | > 260 |
| Flame Resistance | | | | |
| @ 1.5 mm | | -- | | -- |
| @ 3.0 mm | UL94 | -- | UL94 | -- |
| @ 6.0 mm | | -- | | -- |

www.idicomposites.com

The Americas

IDI Composites International
407 S. 7th Street
Noblesville, IN 46060 U.S.A.
317-773-1766
Fax: 317-773-3877
info@idicomposites.com

IDI Composites International
P.O. Box 400
Road #3, KM 151.8
Aguirre, Puerto Rico 00704
787-853-2186
Fax: 787-853-2187
lcruz@idicomposites.com

Asia/Pacific

IDI Composites International
No. 8, Lane 275, QianPu Road
New Eastern Section of
Sonjiang Industrial Park
Shanghai, 201611 China
86-21-51096910
Fax: 86-21-67601689
rrodriguez@idicomposites.com

IDI Composites International
Shenzhen Company, LTD.
Fucheng Industrial Park, Hongtian
Xingjiao, Sajing Town, Bao An
Shenzhen, China 518125
86-755-27229550
Fax: 86-755-27229554
rrodriguez@idicomposites.com

Europe

IDI Composites International
Unit One, Oldbury Park
Popes Lane
Oldbury, West Midlands
B69 4RG U.K.
44-121-552-0038
Fax: 44-121-543-5377
pqarland@idicomposites.co.uk