

PRODUCT SERIES: PRODUCT DESCRIPTION:

46-16-60 FLAME RESISTANT & LOW SMOKE GENERATION

Properties	Glass Content 34%
	Units
Flexural Strength Test Method: ASTM D-790	45,800 psi
Flexural Modulus Test Method: ASTM D-790	2.32 x 10 ⁶ psi
Tensile Strength Test Method: ASTM D-638	23,200 psi
Tensile Modulus Test Method: ASTM D-638	2.42 x 10 ⁶ psi
Impact Strength-Izod Notched Test Method: ASTM D-256	26.1 ftlb./in.
Moisture Absorption Test Method: ASTM D-570	0.0 - 0.14%
Coefficient of Linear Thermal Expansion Test Method: ASTM D-696	1.23 x 10 ⁻⁵ in./in. °F
Dielectric Strength Test Method: ASTM D-149	444 volts/mil
Arc Resistance Test Method: ASTM D-495	198 seconds
Inclined Plane Tracking Resistance Test Method: ASTM D-2303	> 1,200 mins. @ 2.5Kv
Flammability @ 4.07mm Test Method: UL-94	V-0
Flame Spread (radiant panel index) Test Method: ASTM E-162	14.41
Smoke Emission - Flaming Mode Test Method: ASTM E-662	9.0 optical density (4 mins)
Smoke Toxicity Test Method: BSS 7239	$\begin{array}{cccc} HCl & 0.0 \mbox{ ppm} & Aldehydes & 20.0 \mbox{ ppm} \\ HBr & 0.0 \mbox{ ppm} & NO & 10.0 \mbox{ ppm} \\ HCN & 1.0 \mbox{ ppm} & NO_2 & 1.0 \mbox{ ppm} \\ H_2S & 0.0 \mbox{ ppm} & CO_2 & 9,000 \mbox{ ppm} \\ Vinyl Chloride & 0.0 \mbox{ ppm} & CO & 450 \mbox{ ppm} \\ NH_3 & 0.0 \mbox{ ppm} & \end{array}$

The information on this sheet is a guide. The stated values reflect an average of several tests conducted on CI's goods. These values were obtained under ideal conditions and may not be replicated in any particular test, part, or application. Because the values achieved in actual parts depend considerably on part design, molding conditions, and testing methods, no guarantee is made or implied regarding values to be obtained in any specific test, part, or application. CI makes no warranty or representation as to the suitability of any of its goods for use in any application. CI relies on customer to conduct its own tests and judge for itself the suitability of CI's goods. 4/2016

www.idicomposites.com

North America Noblesville, IN Europe Vineuil, France United Kingdom Oldbury, UK Asia/Pacific Shanghai, China Caribbean & South America Aguirre, Puerto Rico Mexico Mexico City, Mexico