

TYPICAL STRUCTURAL FEA PROPERTIES FOR BMC AND SMC

Property	BMC - 15-25% Glass Content		SMC - 20-40% Glass Content	
	US	Metric	US	Metric
Coefficient of Thermal Expansion	10 - 20 x 10 ⁻⁶ °F	17.78 °C	15 - 25 x 10 ⁻⁶ °F	17.78 °C
Flex Modulus	1.4 - 1.7 x 10 ⁶ psi	9.66 - 11.72 GPa	1.5 - 1.9 x 10 ⁶ psi	10.34 - 13.10 GPa
Specific Gravity	1.7 - 2.2 g/cm ³	1.7 - 2.2 g/cm ³	1.6 - 2.0 g/cm ³	1.6 - 2.0 g/cm ³
Poisson's Ratio	0.32 - 0.36 -	0.32 - 0.36 -	0.32 - 0.36 -	0.32 - 0.36 -
Shear Strength	6 - 9,000 psi	41.38 - 62.07 MPa	8 - 12,000 psi	55.17 - 82.76 MPa
Tensile Modulus	1.3 - 1.6 X 10 ⁶ psi	8.97 - 11.03 GPa	1.4 - 1.8 x 10 ⁶ psi	9.66 - 12.41 GPa
Young's Modulus	1.2 - 1.6 x 10 ⁶ psi	8.28 - 11.03 GPa	1.6 - 2.0 x 10 ⁶ psi	11.03 - 13.79 GPa



IDI Composites International
 407 S. 7th Street • Noblesville, IN 46060 U.S.A.
 317-773-1766 • Fax: 317-773-3877 • info@idicomposites.com

www.idicomposites.com